

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

[www.ltslab.co.uk](http://www.ltslab.co.uk)

9630

**TEST CERTIFICATE**

<b>CLIENT:</b>	Camira Fabrics Meltham Mills, Meltham Huddersfield HD9 4AY - - -	<b>Certificate Number:</b>	<b>UK2100600 -1</b>
		<b>Date Received:</b>	19/05/2021
		<b>Date Issued:</b>	27/05/2021
		<b>Issue Number:</b>	<b>1</b>
		Changes made from previous issue (if applicable)	
<b>Contact:</b>	Rebecca Grimes		
<b>Tel:</b>	01924 481366		
<b>Email:</b>	rebecca.grimes@camirafabrics.com		

**SAMPLE IDENTIFICATION**

The information in this section is provided by the client and Lancashire Testing Services Ltd assumes no responsibility or liability for its accuracy.

Sample Name / Reference	Silk
Additional Names:	-
Batch Ref/Number:	467809
Order Number:	11763
Colour:	Arabia
Fabric Composition:	-
Customer:	-

**SPECIFICATION**

BS5867-2:2008 Fabrics for curtains, drapes and window blinds

Type B

**TEST METHOD**

Flammability:	BS EN ISO 15025:2002 - Procedure A -Surface Ignition
Pre-treatment:	12 Standard Commercial Wash Cycles to BS EN ISO 10528 at 75°C, Tumble dried in accordance with ISO 26330:1994 *Exhaust temperature uncalibrated

**Conclusion**

The sample tested: **Complies** with the flammability requirements of:  
 BS5867-2:2008 Type B before and after washing procedures as stated  
 Taking into account uncertainty of measurement  
 Measurements of uncertainty: Time ±1 second, Dimension ±1mm

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

[www.ltslab.co.uk](http://www.ltslab.co.uk)

9630

**TEST CERTIFICATE****Test Results:-****BS5867-2:2008 Fabrics for curtains, drapes and window blinds****Type B**

"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."

Sample Code	UK2100600 -1					
Sample Name / Reference	Silk					
Client	Camira Fabrics					
Date of test	27/05/2021					
Pre-Treatment	BS EN ISO 10528:1995:12 Commercial wash cycles at 75°C Tumble Dried in accordance with BS EN 26330:1994					
Test Conditions	Period h	Temperature °C		Relative humidity %	Air Flow m/s	Volume m <sup>3</sup>
Conditioning of test specimens	≥24	20±2		65±5	-	-
Testing conditions	-	10-30		15-80	≤0.2	≥4
Flame Application time	15 second Face burn			Flame Height (vertical)		40 ± 2mm
Sample size	200 x 160mm			Fabric face tested		Outer
Longest Dimension	Machine Direction			Cross Direction		
As Supplied	1↑	2↓	3↑	4→	5←	6→
Duration of Afterflame (s)	0	0	0	0	0	0
Duration of Afterglow (s)	0	0	0	0	0	0
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming Debris	No	No	No	No	No	No
Damage length Horizontal (mm)	27	27	28	28	27	29
Damage length Vertical (mm)	37	39	39	42	38	39
<b>RESULT:</b>	<b>PASS</b>					

After Wash Procedures	1↑	2↓	3↑	4→	5←	6→
Duration of Afterflame (s)	0	0	0	0	0	0
Duration of Afterglow (s)	0	0	0	0	0	0
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming Debris	No	No	No	No	No	No
Damage length Horizontal (mm)	26	27	27	29	31	28
Damage length Vertical (mm)	40	35	37	36	38	36
<b>RESULT:</b>	<b>PASS</b>					
Deviation from specified procedure:	Exhaust temperature of tumble dryer uncalibrated					

Please note that copies of this original certificate are not valid

**Issue Number: 1**

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality



**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

[www.ltslab.co.uk](http://www.ltslab.co.uk)



9630

On behalf of Lancashire Testing Services :

Tony Alcock,  
Laboratory Technician:

John Marsh,  
Laboratory Technician:



Peter Collings,  
Operations Manager:

If the measurement result plus/minus the expanded uncertainty with a 95 % coverage probability overlaps the limit, it is not possible to state compliance or non-compliance. The measurement result and the expanded uncertainty with a 95 % coverage probability will then be reported. The report will include the actual value with the uncertainty range.