



TEST REPORT

Client: Camira Transport Fabrics Limited
The Watermill
Wheatley Park
Mirfield
WF14 8EH

Entry No: 87286-02

Date received: 13/07/2017

Client's Description: Sample of fabric: Aura – Twist, Colour - CCQC14, Run – 344966, Call 5884 and Call 5881

Test Required: Colour Fastness To Rubbing

Conditioning: In accordance with BS EN ISO 139: 2005 for a minimum of 24 hours at 65+/-4%, Relative Humidity, 20+/-2°C

Date Tests Completed: 21/07/2017

Colour Fastness to Rubbing: BS EN ISO 105–X12: 2002

	<u>Dry</u>	<u>Wet</u>
Warp Way	4-5	4
Weft Way	4-5	4-5

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein

Vivienne Brockbank
Technician
08 August 2017

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
 - ❖ Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
 - ❖ Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104