

## TEST REPORT

<b>Report Ref.</b>	LEI19013064A Original		
<b>Date Received</b>	18/01/2019	<b>Date Issued</b>	31/01/2019

<b>Company Name &amp; Address</b>	Camira Fabrics Limited Meltham Mills Meltham, Huddersfield, HD9 4AY GBR
<b>Contact Name</b>	Greta Ziaugraite

<b>Order Number</b>	83A02445
<b>Sample Description</b>	Hi -Tech
<b>Ref / Style Number</b>	HASNOOF400
<b>Colour</b>	Charcoal (HASOOO)
<b>Quality</b>	Hi -Tech
<b>Batch Number</b>	405377 (0301)
<b>End Use</b>	Contract Upholstery
<b>Quoted Fibre Composition</b>	60% Polypropylene 29% Wool 10% Viscose 1% Carbon Fibre
<b>Retailer</b>	General

Test	Method	Sample	Result
Martindale Abrasion	BS EN ISO 12947-2: 2016		Not Applicable

Tests marked (^) in this report have been performed by an approved 3rd party laboratory.  
Tests marked (\*) in this report are not included in our UKAS scope of accreditation.



Michelle Towers  
(Technician)

**Martindale Abrasion BS EN ISO 12947-2: 2016**  
**Conditioning Parameters: 20°C±2°C & 65% rH±4% rH**

			Requirement
Test load: 12KPA			
Shade Change @ 3,000	4 - 5		
	No fabric breakdown @	Fabric breakdown @	
Head 1	79,000	80,000	
Head 2	79,000	80,000	
Head 3	79,000	80,000	
Average fabric breakdown	79,000		

Overall Test Result: Not Applicable  
Uncertainty: ±17%

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.*

*The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of  $k = 2$ , providing a level of confidence of approximately 95 %. Any Pass/Fail statements do not take into account the Measurement of Uncertainty. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are close to Specification Limits / Requirements.*