



LANCASHIRE TESTING SERVICES LIMITED

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk



9630

TEST CERTIFICATE

CLIENT:	Camira Fabrics Meltham Mills, Meltham Huddersfield HD9 4AY - -	Certificate Number:	UK2000052 -2
		Date Received:	14/01/2020
		Date Issued:	22/01/2020
		Issue Number:	1
Contact:	Luke Russell	Changes from previous issue (if applicable)	
Tel:	01924481368		
Email:	luke.russell@camirafabrics.co		

SAMPLE IDENTIFICATION

Sample Name / Reference: Urban I2
Order / Batch No: 83A07272
Customer: -
Fabric Composition: -
Colour: D9078I
Quality: 436237
Width: -

SPECIFICATION

BS7176:2007 + A1:2011 - Medium Hazard

TEST METHOD

Flammability: BS EN 1021-1:2006 Part 1: Ignition source smouldering cigarette
BS EN 1021-2:2006 Part 2: Ignition source match flame equivalent
BS 5852:2006 Crib Ignition source 5
Pre-treatment: BS 5852:2006 Annex E - Water soaking procedure

Conclusion

The composite tested: **Complies** with the flammability requirements of:
BS 7176:2007 + A1:2011 Medium hazard, taking into account uncertainty of measurement.

Please note that copies of this original certificate are not valid

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk

9630

TEST CERTIFICATE**Test Results:-****BS7176:2007 + A1:2001 - Medium Hazard - Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites***"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."*

Sample Code	UK2000052 -2					
Sample / Name Reference	Urban I2					
Client	Camira Fabrics					
Date of test	22/01/2020					
Pre-Treatment	BS 5852:2006 Annex E - Water soaking procedure Line Dried during at ambient temperature					
Filling Type	Carpenter/RX36110 CMHR polyurethane foam of approximate density 36Kg/m3					
Size of test rig	Small: Back - 450 x 300 ± 2mm + Seat - 450 x 150 ± 2mm					
Test Conditions	Period h	Temperature °C	Relative humidity %	Air Flow m/s	Volume m ³	
Conditioning of test specimens	≥16	23±2	50±5	-	-	
Testing conditions	-	10-30	15-80	0.02-0.2	>6	
Testing Source	BS EN 1021-1:2006 Smouldering Cigarette Source					
Testing time limit	60 minutes after placement of smouldering cigarette.					
Test No.	Position	Ignition/N on Ignition	Duration of: (min.sec)			Smouldering and flaming criteria exceeded: (If any)
			Ignition Source	Flames	Smoke	
1	LHS	NI	19.29	-	20.43	-
2	M	NI	18.56	-	20.18	-
3	-	-	-	-	-	-
Testing Source	BS EN 1021-2:2006 Match flame ignition source					
Testing time limit	2 minutes after removal of burner tube (120 seconds)					
Test No.	Position	Ignition/N on Ignition	Duration of: (sec)			Smouldering and flaming criteria exceeded: (If any)
			Ignition Source	Flames	Smoke	
1	RHS	NI	15	17	43	-
2	M	NI	15	17	43	-
3	LHS	NI	15	16	33	-
RESULT:	SMOULDERING CIGARETTE SOURCE				PASS	
	MATCH FLAME IGNITION SOURCE				PASS	
KEY: I = Ignition, NI = Non Ignition, LHS = Left hand side, M = Middle, RHS = Right hand side						

Please note that copies of this original certificate are not valid

Issue Number: 1

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk

9630

TEST CERTIFICATE

Test Results:-**BS7176:2007 + A1:2001 - Medium Hazard - Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites***"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."*

Sample Code	UK2000052 -2									
Sample Reference	Urban I2									
Client	Camira Fabrics									
Date of test	22/01/2020									
Pre-Treatment	BS 5852:2006 Annex E - Water soaking procedure Line Dried during day at ambient temperature									
Filling Type	Carpenter/RX36110 CMHR polyurethane foam of approximate density 36Kg/m3									
Size of test rig	Large: Back - 450 x 450 ± 2mm + Seat - 450 x 300 ± 2mm									
Test Conditions	Period h	Temperature °C	Relative humidity %	Air Flow m/s	Volume m ³					
Conditioning of test specimens	≥16	23±2	50±5	-	-					
Testing conditions	-	10-30	15-80	0.02-0.2	>20					
Testing Source	BS 5852:2006 Crib Ignition source 5									
Testing time limit	10 minutes after ignition of crib. Observed for 60 minutes in total.									
Test No.	Position	Ignition/NI on Ignition	Duration of: (min.sec)		Extent of Damage to component: mm					
			Flames	Smoke	Horizontal			Vertical		
					Width	Length	Depth	Width	Depth	
1	M	NI	3.55	8.36	124	114	57	144	60	
2	M	NI	4.11	7.19	118	124	55	153	57	
RESULT:		CRIB IGNITION SOURCE 5					PASS			
KEY: I = Ignition, NI = Non Ignition, LHS = Left hand side, M = Middle, RHS = Right hand side										

Test No.	Time for: (sec)		
	Ignition of test pieces	Cover Splitting	Extinction
1	-	-	-
2	-	-	-

On behalf of Lancashire Testing Services :

Tony Alcock,
Laboratory Technician:John Marsh,
Laboratory Technician:Peter Collings,
Operations Manager:

Please note that copies of this original certificate are not valid

Issue Number: 1

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality