

Our Ref: SW/LS/BR

14 June 2018

**Report 322533**


**Page 1 of 2**

Camira Fabrics Limited  
Meltham Mills  
Meltham  
West Yorkshire  
HD9 4AY

Contact: Rebecca Grimes; Katy Longstaff

---

DATE RECEIVED	: 8 JUN 2018
QUALITY/REFERENCE	: BLOSSOM
REPUTED FIBRE CONTENT	: NOT GIVEN
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: PETAL
STYLE NUMBER	: 351111
ORDER NUMBER	: 64904
PERFORMANCE STANDARD	: GENERAL



---

REQUEST: Hydrostatic head

---



**S. WISEMAN**  
**LABORATORY DIRECTOR**

**L. SHERIDAN**  
**LABORATORY MANAGER**

*This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.*



118 Lupton Avenue Leeds LS9 6ED  
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk  
Registered No. 2899980 VAT No. 613 4310 86

**Report 322533**

**PHYSICAL**

**BS EN 20811:1992 (1996) Hydrostatic Head**

Sample area	100cm <sup>2</sup>
Test atmosphere	20°C 65% R.H
Water temperature	20°C
Rate of rise of water pressure	60cm/1min

Test 1	>400 cms/H <sub>2</sub> O
Test 2	>400 cms/H <sub>2</sub> O
Test 3	>400 cms/H <sub>2</sub> O
Test 4	>400 cms/H <sub>2</sub> O
Test 5	>400 cms/H <sub>2</sub> O
Mean	>400 cms/H <sub>2</sub> O

---